

# Madoc Terrazzo Aggregates – Technical Data

	Bulk SG	Absorption %	Micro- Deval	MgSO <sub>4</sub> Soundness
Black Stallion	2.700	0.50%	14.6%	4.6%
Glacier Gray	2.833	0.31%	14.2%	2.3%
Tuscan Cider	2.851	0.36%	12.8%	3.2%
Pepper Harvest	2.843	0.33%	10.8%	8.1%
Chocolate Heritage	2.725	0.40%	9.9%	7.6%
New Royal Green	2.754	0.53%	9.4%	2.5%
Mocha	2.714	0.44%	8.4%	3.4%
Salmon	2.695	0.65%	26.8%	11.0%
Midnight Black Granite	2.824	0.25%	8.3%	1.2%
Georgia White Marble	2.752	0.58%	18.3%	12.8%
Madoc White Marble	2.582	0.82%	16.0%	24.6%

Black Stallion
Glacier Gray
Tuscan Cider
Pepper Harvest
Chocolate Heritage
New Royal Green
Mocha
Salmon
Midnight Black Granite
Georgia White Marble
Madoc White Marble

Average Values	2.752	0.47%	13.59%	7.39%
----------------	-------	-------	--------	-------

- All aggregates tested using MgSO<sub>4</sub> test method except  
Midnight Black Granite which was tested using Freeze-thaw method.
- MgSO<sub>4</sub> Soundness loss max. 12.0% for Pavement, structures, sidewalks, curb & gutter and base
- Micro-Deval max loss 20% for concrete structures, sidewalks, etc.